

## THE EFFECT OF RELATIVE CONCENTRATION OF NO AND O<sub>2</sub> IN A THREE COMPONENT NO-CO-O<sub>2</sub> REACTION FOR THE ELEY-RIDEAL MECHANISM

\*A.U. QAISRANI, M. KHALID and B.Y. AKHTAR

Department of Physics, Gomal University, D.I. Khan, Pakistan

(Received March 09, 2012 and accepted in revised form May 07, 2012)

---

Monte Carlo simulations have been used to explore the effect of the Eley-Rideal (ER) mechanism for three component CO-NO-O<sub>2</sub> heterogeneous catalytic reaction on hexagonal lattice. The system is studied for CO and XO; where XO is NO and O<sub>2</sub> with ratio NO:O<sub>2</sub>. The effect of ratio NO:O<sub>2</sub> on the catalytic reduction of NO into N and O and oxidation of CO to CO<sub>2</sub> are introduced into the model. Many observations are recorded in this three component reaction. It is observed that with the inclusion of ER mechanism with the Langmuir-Hinshelwood (LH) mechanism, a second order phase transition is eliminated and production of CO<sub>2</sub> and N<sub>2</sub> starts as soon as the CO partial pressure departs from zero. The phase diagrams of the surface coverage with CO, N, O and the steady state production of CO<sub>2</sub> and N<sub>2</sub> are shown as a function of partial pressure of CO in the gas phase.

**Keywords:** Catalysis, Three-component surface reaction, Monte Carlo simulation, Eley-Rideal mechanism.

---

### 1. Introduction

The three-component CO-NO-O<sub>2</sub> catalytic reaction is more complex than two-component CO-NO and CO-O<sub>2</sub> catalytic reaction. These three gases CO, NO and O<sub>2</sub> are present all together in different ratios in automobile exhaust. The conversion of poisonous CO(g) and NO(g) into harmless CO<sub>2</sub>(g) and N<sub>2</sub>(g) is important to reduce the pollution of atmosphere. This is done by the oxidation of CO with O<sub>2</sub> and reduction of NO with CO on a suitable metal catalyst. Due to the complexity of three-component reaction, not many studies have been carried out for the understanding of surface process, which includes adsorption of reactants, ratio of reactants and surface reaction. The elementary catalytic reactions steps can best be understood by using computational techniques. The technique of Monte Carlo (MC) simulation can be applied for analyzing certain very important aspects of the reaction, under consideration. Ziff, Gulari and Barshad [1] introduced a Monte Carlo simulation technique now popularly known as the ZGB model to study the oxidation of CO by the  $2\text{CO} + \text{O}_2 \rightarrow 2\text{CO}_2$  reaction on catalytic surface. In this model a square lattice represents the surface and the reaction occurs via Langmuir-Hinshelwood (LH) mechanism (thermal process). In LH mechanism, both reactants are initially adsorbed on the surface and are in thermal

equilibrium with the substrate. The ZGB model exhibits two irreversible phase transitions at  $y_1$ (continuous) and  $y_2$ (discontinuous). Here  $y_1$  is the critical concentration of CO at which steady reactive state (SRS) starts, while  $y_2$  is the critical concentration of CO where the SRS stops. In this model the transition at  $y_1 = 0.389 \pm 0.001$ , separates an oxygen poisoned state from SRS, while a transition at  $y_2 = 0.525 \pm 0.001$  separates the CO poisoned state from the SRS. To investigate the effect of lattice type on the reaction, Meakin and Scalapino [2] examined the behaviour of the ZGB model of CO – O<sub>2</sub> reaction on a hexagonal lattice (each site has six nearest neighbours (nn)). They found  $y_1 = 0.360 \pm 0.005$  and  $y_2 = 0.51 \pm 0.001$  for the same reaction on hexagonal surface.

Yaldram and Khan [3, 4] applied the ZGB model to study the CO-NO reaction on square and hexagonal lattice. The importance of the type of lattice for CO-NO reaction system was one of the obvious conclusions of their work. They found that simple LH mechanism does not produce SRS, while SRS exists for hexagonal lattice. They found that the second order phase transition (SOPT) takes place at  $y_1 = 0.185 (\pm 0.002)$  and first order phase transition (FOPT) takes place at  $y_2 = 0.338 (\pm 0.002)$ .

---

\* Corresponding author : au.qaisrani52@yahoo.com

Yaldram and Khan [3, 4] used the simple LH mechanism for CO-NO reaction. This simple LH mechanism has been used by number of authors to study the different aspects of this reaction system [5-9]. It has been emphasized by many authors that non-thermal processes are also important to understand the catalytic reactions [10-14]. These processes include the Eley-Rideal (ER) mechanism (a direct reaction between a gas phase atom and an adsorbed atom) and the precursor mechanism of the surface reactions. Where, the precursor mechanism involve direct collisions between chemisorbed species and molecules or atoms that are trapped in the neighbourhood of the surface but have not been thermalized. Meakin [15] has also explored the effect of ER process on the simple ZGB model for the catalytic oxidation of CO by oxygen. Following the ZGB model, several attempts have been made to study different aspects of the CO-NO catalytic reaction system [16-18]. However, relatively less attention has been paid to study the three-component CO-NO-O<sub>2</sub> heterogeneous catalytic reaction through computer simulation.


Yaldram and Khan [19] presented a model for the three-component CO-NO-O<sub>2</sub> reaction on a hexagonal surface. They concluded that the catalytic surface is more efficient in giving a larger SRS in the three-component CO-NO-O<sub>2</sub> reaction than in the respective two-component CO-NO and CO-O<sub>2</sub> reaction. Waqar and Albano [20] presented a model for the three-component reaction on square surface. They showed that the system became YK model when the concentration of oxygen was zero, while it became ZGB model when the concentration of NO was zero. They also showed that with the addition of NO in CO-O<sub>2</sub> reaction, the critical points shifted towards lower values of CO partial pressure, whereas the addition of O<sub>2</sub> in the CO-NO reaction shifted the critical points towards higher values of CO partial pressure. Basit and Waqar [21] showed that with the addition of ER mechanism, position of critical points were not the same as seen in the LH mechanism for square surface.

The main objective of this manuscript is to explore the effects of variation of NO and O<sub>2</sub> concentration alongwith ER mechanism on the phase diagram of the LH model for the three-component CO-NO-O<sub>2</sub> catalytic reaction on hexagonal lattice through Monte Carlo Simulation. In the next section (2), the reaction scheme of the

system and simulation procedure is outlined. Results are presented and discussed in Section 3. Finally, the conclusions are presented in Section 4.

## 2. Model and Simulation

According to LH mechanism, it is assumed that the CO-NO-O<sub>2</sub> reaction occurs according to the following steps :



Whenever Eley-Rideal mechanism is taken into the consideration then following step is included in simulation model.



Here (g) refers to the gas phase, S is an empty surface site and X<sup>S</sup> represents the chemisorbed X-species on the surface. We consider an infinite reservoir filled with CO, NO and O<sub>2</sub> gas molecules with partial pressures (concentrations) y<sub>CO</sub>, y<sub>NO</sub> and y<sub>O<sub>2</sub></sub> respectively. The ratio (NO:O<sub>2</sub>) is kept fixed, while the ratio of third component (CO) is varied relative to the sum of other two in such a way that y<sub>CO</sub> + y<sub>NO</sub> + y<sub>O<sub>2</sub></sub> = 1. As such the reaction of CO with the mixture of NO and O<sub>2</sub> is taken with all concentration of y<sub>CO</sub> from 0 to 1.0 The reservoir is in contact with the surface which is simulated by means of a hexagonal lattice of linear dimension L = 64. It has been shown that an increase in lattice size does not affect the overall qualitative feature of the phase diagram; it slightly changes the critical values [22]. Periodic boundary conditions are applied in order to avoid the boundary effects. The simulation starts with a clean surface and proceeds as follows:

A trial begins with random collision of a gas molecule of one of the reactants with probability y<sub>CO</sub> or 1 - y<sub>NO</sub> - y<sub>O<sub>2</sub></sub> on the surface of hexagonal lattice. A surface site is chosen randomly and for this chosen site there are two possibilities, i.e, the site is either empty or occupied. For randomly selected site, one of the following events may occur :

- a. If the selected site is empty and CO happens to be selected, then CO is adsorbed on the surface as  $(\text{CO}^{\text{S}})$  via step (1). Six nearest neighbouring (nn) sites of the adsorbed CO molecule are scanned randomly for the presence of  $\text{O}^{\text{S}}$ . If any one of the nn sites is occupied by  $\text{O}^{\text{S}}$  then the reaction step (4) takes place with the creation of two vacant sites on the surface.
- b. If CO happens to be selected and the randomly selected site is already occupied by  $\text{CO}^{\text{S}}$  or  $\text{N}^{\text{S}}$ , then trial ends. If the selected site is occupied by an  $\text{O}^{\text{S}}$  atom, then the CO (g) molecule in gas phase directly reacts with  $\text{O}^{\text{S}}$  with some probability  $P_{\text{ER}}$  in order to complete the ER step (5). In this case only one site gets vacated.
- c. If NO happens to be selected and the randomly selected site is already occupied, then trial ends. On the other hand, if the randomly selected site is empty and NO happens to be selected, then one of nearest neighbouring sites of the vacant site is selected randomly. If the site is occupied, then the trial ends; otherwise NO is dissociated and adsorbed on to these two empty sites via reaction step (2). The dissociation rate of NO into N and O are taken to be 100%. The choice for adsorption on these two sites for N and O is made randomly. Once N and O are adsorbed, the nearest neighbours of each are scanned for the presence of  $\text{N}^{\text{S}}$  or  $\text{CO}^{\text{S}}$  in order to complete reaction steps (3) and (4) respectively. If  $\text{N}^{\text{S}}$  is surrounded by more than one  $\text{N}^{\text{S}}$ , the one pair of  $\text{N}^{\text{S}}-\text{N}^{\text{S}}$  is selected randomly to give  $\text{N}_2(\text{g})$  and two sites are vacated. Similarly one pair of  $\text{CO}^{\text{S}}-\text{O}^{\text{S}}$  or  $\text{CO}(\text{g})-\text{O}^{\text{S}}$  is selected randomly to give  $\text{CO}_2(\text{g})$ .
- d. If  $\text{O}_2$  happens to be selected and if the randomly selected site is occupied, then the trial ends. In case the randomly selected site is vacant, then another vacant site is required to adsorb the  $\text{O}_2$  molecule in atomic form. If it finds the second vacant site from the six nn site, then  $\text{O}_2$  molecule dissociates into two O atoms which are adsorbed on the surface. After adsorption, the nn sites of these two  $\text{O}^{\text{S}}$  atoms are scanned for the presence of  $\text{CO}^{\text{S}}$  to complete the reaction step (4). If two or more pairs of  $\text{CO}^{\text{S}}-\text{O}^{\text{S}}$  exist, then reaction will take place by random selection of one pair of  $\text{CO}^{\text{S}}-\text{O}^{\text{S}}$ . If reaction does not take place between  $\text{CO}^{\text{S}}-\text{O}^{\text{S}}$ , then  $\text{O}^{\text{S}}$  will reside on the surface and the next MC cycle starts again.

The simulations are carried out on Pentium 4 -

PC. The step length for  $y_{\text{CO}}$  is taken as 0.05, except close to the transition points. In Tables 1 & 2, the step length close to the transition points  $y_1$  and  $y_2$ , are taken as 0.001 for precise determination of transition points. However, with the inclusion of ER step probability, the step size close to the transition points  $y_1$ , is taken as 0.005, whereas the step size of 0.001 is taken close to the transition point  $y_2$ . The equilibrium coverages are measured as a function  $y_{\text{CO}}$ . To locate the critical points, ten independent, runs each up to 50000 Monte Carlo (MC) cycles, are carried out. One MC cycle is equal to  $L \times L$  trials. If all the ten runs proceed up to 50000 cycles without the lattice becoming poisoned (fully occupied), the particular point is considered to be within SRS. The poisoning of even a single run is a sufficient criterion for considering the point to be in the poisoned state. If the run does not end up in a poisoned state, then in order to get the coverages in SRS, the initial 10000 MC are disregarded and averages are taken over the subsequent 40,000 MC cycles. The values of coverages (production rate) are obtained after 10 MC cycles, so that the final coverage (production) is an average taken over 4000 configurations.

### 3. Results and Discussions

The earlier work for CO- $\text{O}_2$  [2] and CO-NO [3, 4] reactions on hexagonal lattice using LH mechanism is well known. The values of transition points,  $y_1$  and  $y_2$  for CO- $\text{O}_2$  reaction are  $0.360 \pm 0.005$  and  $0.51 \pm 0.001$  respectively. Whereas the values of transition points  $y_1$  and  $y_2$  for CO-NO reaction are  $0.185 \pm 0.002$  and  $0.338 \pm 0.001$  respectively. In this manuscript the LH mechanism is combined with ER mechanism. Here we have investigated the effect of concentration of ratio of NO: $\text{O}_2$  in the three-component CO-NO- $\text{O}_2$  reaction. In the LH mechanism, for zero concentration of NO, three-component CO-NO- $\text{O}_2$  system behaves like CO- $\text{O}_2$  reaction, while for zero concentration of  $\text{O}_2$ , three-component CO-NO- $\text{O}_2$  system behaves like CO-NO reaction. It confirms the findings of Waqar [20] and Basit [21]. Table 1 shows the transition points and the window width versus NO: $\text{O}_2$  in the mixture according to LH mechanism. In the first row of this table, when the concentration of the both NO and  $\text{O}_2$  are equal, the production of  $\text{CO}_2$  and  $\text{N}_2$  starts at  $y_{\text{CO}} \approx 0.28$ . Here system enters SRS which is consistent with the work of Yaldrum and Khan [19]. Table 1 shows the

transition points and window width versus NO:O<sub>2</sub> in the mixture in the LH mechanism.

Table1. (Reaction steps 1-4) when the concentration of O<sub>2</sub> is increased and concentration of NO is fixed in LH mechanism.

Ratio NO : O <sub>2</sub>	y <sub>1</sub> ±0.001	y <sub>2</sub> ±0.001	MPR of CO <sub>2</sub>	MPR of N <sub>2</sub>	Window Width
1 1	0.283	0.436	0.196	0.0327	0.153
1 2	0.315	0.460	0.206	0.0206	0.145
1 3	0.330	0.472	0.210	0.0150	0.142
1 4	0.334	0.478	0.211	0.0117	0.144
1 5	0.341	0.483	0.213	0.0097	0.142
1 6	0.344	0.486	0.214	0.0082	0.142
1 7	0.346	0.488	0.214	0.0072	0.142
1 8	0.349	0.490	0.215	0.0063	0.141
1 9	0.353	0.492	0.216	0.0057	0.139

It is observed that in the LH mechanism, with the increase of O<sub>2</sub> concentration in the three-component CO-NO-O<sub>2</sub> reaction, the transition points, y<sub>1</sub> and y<sub>2</sub> are shifted towards higher concentration of CO. Consequently the window width decreases. Moreover, as the concentration of O<sub>2</sub> increases, the maximum production rate of CO<sub>2</sub> increases slowly. Simultaneously production rate of N<sub>2</sub> slowly decreases (Table 1). With the increase of O<sub>2</sub> in NO:O<sub>2</sub> (relatively decreasing the concentration of NO in the mixture) leads to lesser production of N<sub>2</sub>. It confirms the findings of Yaldram and Khan [19]. The trends of y<sub>2</sub>, the window width (ww) and maximum production rate versus NO/O<sub>2</sub> are shown in Fig.1. Table 2 shows the transition points and the window width versus NO:O<sub>2</sub> in the mixture according to LH mechanism.

Moreover, it is noted from Table 2, that with the increase of NO concentration in the three-component CO-NO-O<sub>2</sub> reaction, the transition points, y<sub>1</sub> and y<sub>2</sub> move towards lower concentration of CO, for the case of LH mechanism. Simultaneously the window width increases slightly. Table 2 indicates that as the relative concentration of NO in the mixture increases, the production of CO<sub>2</sub> decreases. It is consistent with the findings of Grahm et al. [23], while production rate of N<sub>2</sub> slowly increases. Moreover, for zero concentration of O<sub>2</sub> in the mixture, the first transition occurs at y<sub>1</sub> =

0.186, while the second transition occurs at y<sub>2</sub> = 0.339. It confirms YK model [3].




Figure 1. Trends of critical points y<sub>2</sub>(solid circle), y<sub>1</sub> (solid square), window width(solid diamond), MPR of CO<sub>2</sub> (solid up triangle), N<sub>2</sub> (solid down triangle) versus NO/O<sub>2</sub> in LH mechanism.

Table 2. (Reaction steps 1-4) when the concentration of NO is increased and concentration of O<sub>2</sub> is fixed in LH mechanism.

Ratio NO : O <sub>2</sub>	y <sub>1</sub> ±0.001	y <sub>2</sub> ±0.001	MPR of CO <sub>2</sub>	MPR of N <sub>2</sub>	Window Width
1 1	0.283	0.436	0.196	0.0327	0.153
2 1	0.252	0.407	0.188	0.043	0.155
3 1	0.234	0.393	0.184	0.051	0.159
4 1	0.224	0.382	0.179	0.057	0.158
5 1	0.218	0.376	0.176	0.067	0.158
6 1	0.210	0.371	0.171	0.067	0.161
7 1	0.205	0.369	0.171	0.068	0.164
8 1	0.202	0.365	0.170	0.068	0.163
9 1	0.200	0.363	0.168	0.069	0.163

In order to understand the effect of NO:O<sub>2</sub> on LH mechanism alongwith ER mechanism on hexagonal lattice for three component CO-NO-O<sub>2</sub> reaction, we have considered three cases with varying y<sub>CO</sub>:

- i. When the concentration of NO = concentration of O<sub>2</sub>
- ii. When the concentration of NO < concentration of O<sub>2</sub>
- iii. When the concentration of NO > concentration of O<sub>2</sub>

Case (i) for  $NO = O_2$

Fig. 2 shows the phase diagram of the surface coverage and production rate of  $CO_2$  and  $N_2$  for case (i) when ER-step probability  $P_{ER}$  of 0.1 is introduced with LH model. It shows that for  $y_{CO} = 0$ , 83% of the surface is covered with oxygen, 10% of the surface is covered with nitrogen and the other 7% isolated vacancies are randomly distributed on the surface. With the addition of a very small amount of CO ( $y_{CO} = 0.005$ ) and ER-step probability of 0.1, the system enters the SRS with




Figure 2a Phase diagram with coverages of surface oxygen (open circles), CO (open triangles), N (stars) for  $NO:O_2 = 1:1$  and ER step probability of 0.1.




Figure 2b. Production of  $CO_2$  (closed squares) and  $N_2$  (open squares) for  $NO:O_2 = 1:1$  and ER step probability of 0.1.

continuous production of  $CO_2$  and  $N_2$ . This is because at  $y_{CO} = 0.005$ , the surface is covered with about 83% of oxygen atoms and therefore ER-mechanism becomes effective and fast in this region with high coverage of adsorbed oxygen and this observation is consistent with the experimental observations [24,25]. Initially, to locate the first transition point  $y_1$ , the lowest value of  $y_{CO}$  considered in the simulation was  $y_{CO} = 0.005$ . At this value the system enters the SRS. We therefore assume that the reactive state starts immediately for a non-zero value of  $y_{CO}$ . Since with the inclusion of a very small amount of CO ( $y_{CO} = 0.005$ ), the production of  $CO_2$  and  $N_2$  starts, we therefore, conclude that this fact leads to the elimination of  $y_1$  (SOPT). With further increasing the concentration of CO, the production of  $CO_2$  and  $N_2$  increases till the first order phase transition (FOPT) stops the catalytic activity at  $y_{CO} = 0.427 (\pm 0.001)$  and the surface is poisoned with a combination of CO and N. At  $y_{CO} = 0.427 (\pm 0.001)$ , the coverage of CO on the surface increases suddenly and jumps to a large value ( $\approx 0.878$ ). For  $y_{CO} < y_2$ , the coverage of N on the surface decreases more slowly than the coverage for  $y_{CO} > y_2$ .

Case (ii) for  $NO < O_2$ :

As we increase the concentration of oxygen in the mixture of NO and  $O_2$  in the ratio of  $NO:O_2$  from 1:1 to 1:9, the transition points  $y_2$  move from 0.427 to 0.484 (Table 3). The results presented in Tabular form (Table 3) are again presented graphically in Fig. 3. These results indicate that the width of reactive region increases with the increase of  $O_2$  concentration in the mixture of reactants.

Table 3. (Reaction steps 1-5) when the concentration of  $O_2$  is increased and concentration of NO is fixed in ( $NO : O_2$ ), when ER-step probability  $P_{ER} = 0.1$ .

Ratio NO : $O_2$	$y_1$	$y_2$ $\pm 0.001$	MPR of $CO_2$	MPR of $N_2$
1 1	0.0	0.427	0.221	0.037
1 2	0.0	0.455	0.227	0.023
1 3	0.0	0.468	0.239	0.019
1 4	0.0	0.474	0.241	0.016
1 5	0.0	0.478	0.242	0.012
1 6	0.0	0.481	0.243	0.010
1 7	0.0	0.483	0.244	0.008
1 8	0.0	0.485	0.245	0.009
1 9	0.0	0.486	0.259	0.006




Figure 3. Trend of  $y_2$  (solid square) and production of  $\text{CO}_2$  (solid circle) &  $\text{N}_2$  (solid up triangle) versus  $\text{NO}/\text{O}_2$  with ER step probability of 0.1.

It can be seen that with the increase of  $\text{O}_2$  concentration,  $y_2$  shifts towards higher concentration of CO.

Fig. 4 shows the phase diagram of the surface coverage and production rate of  $\text{CO}_2$  and  $\text{N}_2$  when the ratio for  $\text{NO}:\text{O}_2$  is of 1:9. It is also observed that with the increase of concentration of  $\text{O}_2$  in the mixture, the maximum production rate (MPR) of  $\text{CO}_2$  increases whereas production of  $\text{N}_2$  decreases and these observations are shown in Table 3. The rise of production rate of  $\text{CO}_2$  can be explained on the basis that enough oxygen becomes available to yield  $\text{CO}_2$  production.




Figure 4a. The same as in Fig.2 (a) but for  $\text{NO}:\text{O}_2 = 1:9$  and ER step probability of 0.1.




Figure 4b. The same as in Fig. 2(b) but for  $\text{NO}:\text{O}_2 = 1:9$  and ER step probability of 0.1.

Therefore for a better catalyst, some mechanism should be developed in exhaust chamber to supply sufficient amount of oxygen to ensure the consumption of oxygen and NO before escaping into the atmosphere.

Case (iii) for  $\text{NO} > \text{O}_2$ :

Table 4. (Reaction steps 1-5) when the concentration of  $\text{O}_2$  is fixed and concentration of NO is increased in ( $\text{NO} : \text{O}_2$ ), when ER-step probability  $P_{ER} = 0.1$ .

Ratio $\text{NO} : \text{O}_2$	$y_1$	$y_2$ $\pm 0.001$	MPR of $\text{CO}_2$	MPR of $\text{N}_2$
1 1	0.0	0.427	0.221	0.037
2 1	0.0	0.402	0.209	0.052
3 1	0.0	0.387	0.202	0.061
4 1	0.0	0.376	0.198	0.065
5 1	0.0	0.370	0.194	0.069
6 1	0.0	0.368	0.192	0.072
7 1	0.0	0.362	0.190	0.074
8 1	0.0	0.360	0.189	0.076
9 1	0.0	0.357	0.188	0.077

It can be seen in Table 4 that maximum production of  $\text{CO}_2$  decreases continuously with the increase of concentration of NO in the mixture which confirms the findings of Grahm et al.[23]. It is noted that by increasing NO concentration, the production of  $\text{N}_2$  also increases. This is due to the dissociation of NO into N and O and hence the coverage of surface with nitrogen increases with

the increase of NO concentration (Fig.5 (a)). After, dissociation, these nitrogen atoms are adsorbed on the surface and  $\text{CO}^{\text{S}}$  molecule is blocked by these atoms. As such,  $\text{CO}^{\text{S}}$  cannot find  $\text{O}^{\text{S}}$  on the surface to yield  $\text{CO}_2$  gas. Therefore, the width of the reactive region decreases with increase in NO concentration in the mixture. It is also noted that when we increase the concentration of NO in the mixture of NO and  $\text{O}_2$  in the ratio of NO: $\text{O}_2$  from 1:1 to 9:1, the coverage of nitrogen becomes higher, while coverage of oxygen becomes lower (Fig. 6). Moreover, with the increase of concentration of NO in the mixture, the transition point  $y_2$  is shifted towards lower concentration of CO (Table 4).




Figure 6. Coverages of surface oxygen vs CO Concentration for NO: $\text{O}_2$  = 1:1 (closed squares); 1:9 (closed circles) and 9:1 (open circles) with ER step probability of 0.1.




Figure 5a. The same as in Fig.2 (a) but for NO: $\text{O}_2$  = 9:1 and ER step probability of 0.1.




Figure 5b. The same as in Fig. 2(b) but for NO: $\text{O}_2$  of 9:1 and ER step probability of 0.1.

#### 4. Conclusion

Yaldram and Khan [19] studied the three components, CO-NO- $\text{O}_2$  as well as the individual two component reactions NO-CO and CO- $\text{O}_2$  on hexagonal lattice. They recorded SRS  $0.185 < y_{\text{CO}} < 0.338$  and  $0.365 < y_{\text{CO}} < 0.585$  for NO-CO and CO- $\text{O}_2$  reactions respectively. They also have shown that a large SRS exists between  $0.185 < y_{\text{CO}} < 0.585$  for purely three-component CO-NO- $\text{O}_2$  reaction with different combinations of NO and  $\text{O}_2$  concentration in the mixture. In this regard they recorded the window width as  $\approx 0.430$  for the three component system. On the other hand, we have carried out a detailed study of ER mechanism for the three-component system CO-NO- $\text{O}_2$  on the hexagonal lattice by varying the concentration of its constituents by Monte Carlo simulation. The ER mechanism in which a reactant (CO) in gas phase directly picks up  $\text{O}^{\text{S}}$  (atom) from the surface and forms the product  $\text{CO}_2$ , adds some interesting features in the phase diagrams of three-component system CO-NO- $\text{O}_2$  that were not seen by considering LH mechanism in YK model [19]. With the introduction of ER mechanism with LH mechanism, a second order phase transition is eliminated and production of  $\text{CO}_2$  and  $\text{N}_2$  starts the moment  $y_{\text{CO}} \neq 0$ . In YK model [19], the SOPT exits, whereas our model eliminates the SOPT due to the addition of ER mechanism on a simple LH model for the CO-NO- $\text{O}_2$  catalytic reaction on a hexagonal lattice. Moreover, we get the width of reactive region (window width) as  $\approx 0.486$  for this three

component system when the ratio for NO:O<sub>2</sub> is 1:9 with ER-step probability  $P_{ER} = 0.1$ . We hope that this study will contribute in the understanding of three component reaction in real system.

### References

- [1] R. M. Ziff, E. Gulari and Y. Barshad, *Phys. Rev. Lett.* **56** (1986) 2553.
- [2] P. Meakin and D. J. Scalapino, *J. Chem. Phys.* **87** (1987) 731.
- [3] K. Yaldram and M. A. Khan, *J. Catal.* **131** (1991) 369.
- [4] K. Yaldram and M. A. Khan, *J. Catal.* **136** (1992) 279.
- [5] J. Cortes, H. Puschman and E. J. Valencia, *Chem. Phys.* **109** (1998) 6086.
- [6] A.G. Dickman, *Phys. Rev. E* **59** (1993) 6361.
- [7] K. Yaldram, K. M. Khan, N. Ahmad and M.A. Khan, *J. Phys A: Math.Gen.* **26L** (1993) 805.
- [8] B. J. Brosilow and R. M. Ziff, *J. Catal.* **136** (1992) 275.
- [9] B. Meng, W. H. Weinberg and J. W. Evan, *Chem. Phys.* **101** (1994) 3234.
- [10] N. O. Wolf, D. R. Burgess and D.K. Hoffman, *Surf. Sci.* **100** (1980) 453.
- [11] S. P. Sing-Boparai, M. Bowker and D. A. King, *Surf. Sci.* **53** (1975) 55.
- [12] G. Comsa, R. David and B. J. Schumacher, *Surf. Sci.* **95** (1980) L210.
- [13] J. Harris, B. Kasemo and E. Tornqvist, *Surf. Sci.* **105** (1981) L281.
- [14] B. Jackson and M. Person, *J. Chem. Phys.* **103** (1995) 6257.
- [15] P. Meakin, *J. Chem. Phys.* **93** (1990) 2903.
- [16] M. Khalid, A. U. Qaisrani and M. K. Khan, *Int. J. Mod. Phys. C* **16** (2005) 1279.
- [17] K. M. Khan and W. Ahmad, *J. Phys A: Math.Gen.* **35** (2002) 2713.
- [18] N. Ahmad and K. M. Khan, *Chem. Phys.* **263** (2001) 339.
- [19] K. Yaldram, K. M. Khan, N. Ahmad and M. A. Khan, *J. Catal.* **147** (1994) 96.
- [20] W. Ahmad and E. V. Albano, *Appl. Surf. Sci.* **254** (2008) 2436.
- [21] A. Basit and W. Ahmad, *J. Korean. Phys. Soc.* **59** (2011) 134.
- [22] K. M. Khan, K. Yaldram, N. Ahmed and Q. Haque, *Physica A* **268** (1999) 89.
- [23] G. W. Graham, A. D. Logan and M. Shelef, *J. Phys. Chem.* **97** (1993) 5445.
- [24] T. Engel and G. Ertl, *Adv. Catal.* **28** (1979) 1.
- [25] C.T. Compbell, G. Ertl, H. Kuipers and J. Segner, *J. Phys. Chem.* **73** (1980) 5862.